

NASA TECH BRIEF



NASA Tech Briefs are issued by the Technology Utilization Division to summarize specific technical innovations derived from the space program. Copies are available to the public from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia, 22151.

Pigmented Coating Resists Thermal Shock

The problem: To provide a coating for space vehicles that will resist the effects of thermal shock and long exposure to direct sunlight.

The solution: A mixture of zinc oxide and potassium silicate calcined for 16 hours at 700°C to form the coating pigment.

How it's done: The calcined pigment materials are mixed in a pigment-to-binder ratio of 4.30:1 with a solids content of 56.9%. A typical batch consists of 100 g of zinc oxide, 50 cc of a 35% solution of potassium silicate, and 50 cc of distilled water. Ball milling follows, using porcelain balls in a dense alumina mill with a volume ratio of ball-to-material of 1:3 and a total charge of less than 50%. A milling time of 6 hours yields a satisfactory consistency for spraying.

Aluminum or plastic substrates must be abraded and thoroughly cleaned prior to spraying. A first coat is lightly applied, using purified nitrogen for pressure, until a reflection due to liquid is apparent. Following

air drying, a second, heavier coat is applied until a glossy finished texture is achieved.

Notes:

1. Satisfactory physical properties are obtained by air drying but improved hardness may be obtained by heat curing at 140°C.
2. Inquiries concerning this innovation may be directed to:

Technology Utilization Officer
Jet Propulsion Laboratory
4800 Oak Grove Drive
Pasadena, California, 91103
Reference: B65-10354

Patent status: NASA encourages commercial use of this innovation. No patent action is contemplated by NASA.

Source: Harold L. Rechter and Yoshiro Harada
of IIT Research Institute under contract
to Jet Propulsion Laboratory
(JPL-SC-083)

Category 03